



High Performance Paint Product Data Sheet



EVO EASYSAND

05-158 JUN 09



DESCRIPTION: Specialised acrylic water based sealer/undercoat.

TYPICAL USES:

INTERIOR: As a sealer/undercoat for plaster board, wood and composite board such as MDF and Tri Board. The level of finish that can be achieved is dependant on the film build and the skill of the applicator. A level 5 finish is achievable.

EXTERIOR: Can be used in some applications where a high fill product is required. Refer to CTL technical department.

PERFORMANCE: Excellent adhesion to substrate. High filling, high build properties and low sink back. Very good hold out for subsequent top coats. Excellent levelling and easy sanding. Can be used as a "filler" on concrete blocks.

LIMITATIONS: Do not apply if the temperature during application and drying is likely to fall below 10°C. Do not apply in very damp humid conditions. Thin coats will not give the desired build and subsequently the finish will be substandard.

TECHNICAL DATA:

Resin:	Specialised acrylic
Solvent:	Water
Finish:	Flat
Colour:	White/Limited Colours
Touch Dry (minimum):	60 minutes @ 20°C
Recoat Time (minimum):	Overnight
Primer:	See over
Number of Coats:	1-2
Dry Film Thickness:	
Wet Film Thickness:	Up to 500 microns
Durability:	
Thinning and Clean Up:	Water
VOC:	
Pot Life:	Not Applicable
Pack Size:	1, 4, 10 Litre

SPREAD RATE:

Theoretical Coverage: 10-12 m²/litre/coat.
Coverage depends on surface profile and porosity.

COMPUTER CODES:

EVO Easysand 05-158

Coating Technologies Limited, 16 Aetna Place, Henderson, Auckland, New Zealand

Phone: 0064 9 837 0897 Fax: 0064 9 837 3736 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

EVO EASYSAND

SURFACE PREPARATION:

(Refer to "Surface Preparation and Paint Systems" for full details). To ensure a successful application all surfaces to be coated must be clean, dry and stable.

All cracks and joints need to be treated as appropriate to suit the situation. Do not expect paint to bridge moving cracks/joints successfully.

Any mould, moss, algae needs to be treated with a suitable chemical cleaner/inhibitor. Ensure surfaces are free from oil, grease and any surface contamination. Use commercial detergent/alkali cleaner, not Acid wash.

Note: Commencement of work on a surface means in general you accept that surface. If any doubt about condition etc, seek advice.

GIB BOARD:

Ensure stopping is completed to a high standard. Sand all surfaces with #150 grit or finer (#220) sand paper. Remove all dust etc. from walls and floors. Spray, roll or brush on a full coat. Allow to dry (overnight). Sand with flat faced sanding tool, #150-220 grit until surface defect free. Fill any minor defects with knifing compound (e.g. Rapid Filler), sand again and fill any defects if present. Do not expose paper of Gib Board.

Note: The appearance should now be uniform in colour and appearance. Stopping should not be visible. Re-apply a light coat if stopping still visible then re-sand.

To achieve a level 5 finish, the preferred method of application is spray, applying a thicker film with minimal surface texture.

Note: Spray applying the first coat as a "light" application followed up with a full coat when tack free, provides a good foundation to sand back on. This "wets out" the surface, minimizes substrate defects and ensures maximum adhesion for EVO EASYSAND.

INTERIOR BLOCKWORK/CONCRETE:

EVO EASYSAND is excellent for filling the pores and providing a good surface for finish coats.

WOOD:

Apply as for Gib Board. Staining can result from the sap of some timbers. ALKYD WOOD PRIMER can be used to reduce this. For MDF etc, apply as Gib Board.

ALL PAINTED SURFACES;

Remove any and all flaking or blistering paint by chemical, mechanical means. Be careful not to create an undue profile or damage the underlying substrate. Repair any damaged areas with suitable plaster/filler. Allow to cure. All surfaces must be clean and free of dust, dirt, grease etc. Check soundness of surface by cross-cutting with a sharp blade and applying tape. Rip tape away. If paint is removed surface is unsound and requires stripping prior to re-painting.

APPLICATION:

Apply by brush, roller or spray. (Needs to be over coated).

SPRAY: Use airless spray (2500psi min), with tip 515/513 approx or larger. Film build can be in excess of 500 microns without sagging, per coat.

ROLLER: Use 6-10 mm nap, dacron roller or similar, applying full coat. Do not roll excessively as this will reduce film build and detract from the final quality of finish.

BRUSH: Use good quality brush. Apply a full coat.

NOTE: Sanding may be undertaken as soon as the EVO EASYSAND is dry, say 2-3 hours at 20°C. It may be left longer (overnight) and will sand easily.

THINNING & CLEAN UP:

Can be thinned up to 10% for ease of application during hot weather. Clean up in water. Use a small amount of detergent to aid clean up.

ENVIRONMENTAL:

The evolution (EVO) range of products are formulated on the latest available resins to give you both high performance and also to meet low VOC (Volatile Organic Compound) levels set out in current local standards. Likewise levels of environmentally harmful substances are either significantly reduced or eliminated. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET.